

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 email: govmark.accounting@sgs.com

Page 1

Received: 10/26	5/2018 Completed: 11/14/2018	Letter: Z4	RV	P.O.#:	Test Report #:	3-29296-4-
	Style: Art. Breeze Fusion. Cont 4811 Violet. Product End Use:		of Nev	w Zealand / 12% Polya	amide. Finish: None. We	eight: 590 g/lm. Color:
Tested For: Bente Ellingsoe, Quality Department			Key Test:	ASTM D 4034/ACT	150	
G	abriel A/S					
H	julmagervej 55			Tel:	011-45-9630-3100	Ext:
D	K-9000 Aalborg, Denmark			Fax:	011-45-9811-6125	

Test Category: Seam Slippage Specifier: ACT LE 2015; V 08/15 PC: 8H dl/SM

NTR 6/16

TEST PERFORMED: ASTM D 4034 - Standard Test Method for Resistance to Yarn Slippage at the Sewn Seam in Woven Upholstery Fabrics - Plain, Tufted, or Flocked --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: Upholstery

ACCEPTANCE CRITERIA: 25 lbf minimum average for warp and weft

SEAM CONSTRUCTION:

Seam Allowance: 0.5"

Seam Type: 301 Lockstitch

Thread Type: 100% Nylon Bonded Monocord;

Needle Thread size 8/Bobbin Thread Size 5

Needle: Size 22 Ball Point

Stitches/Inch:  $7 \pm 0.5$ 

RESULTS: Specimen results reported to the nearest 0.5 lb force (lbf)

Average reported to the nearest 0.5 lb force (lbf)

	Specimen	#	(lbf)
		-	
Warp Yarn Slippage:	1		124.0 SB
(seamed in warp direction)	2		125.0 SB
	3		71.0 SS
	4		92.0 SS
	5		71.0 SS
		Avg:	96.5
Weft Yarn Slippage:	6		82.0 SS
(seamed in weft direction)	7		90.0 SS
	8		81.5 SS
	9		76.0 SS
	10		78.0 SS
		Avq:	81.5

ABBREVIATIONS WHICH MAY BE USED:

SS = Seam Slippage

SB = Seam break before 1/4" slippage FB = Fabric break before 1/4" slippage

FBS = Fabric break at Seam before 1/4" slippage

(Page 1 of 2)



96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 email: govmark accounting@sgs.com

SUS GOVMARK		email: govmark.accounti	ng@sgs.com Page 2
eceived: 10/26/2018 Completed: 11/14/2018 Letter: Z4	RV <b>P.O.</b> #:	Test Report #:	3-29296-4-
Client's Style: Art. Breeze Fusion. Content: 88% Wooldentification 4811 Violet. Product End Use: Upholstery.	ls of New Zealand / 12% F	Polyamide. Finish: None. Weight	: 590 g/lm. Color:
ested For: Bente Ellingsoe, Quality Department	Key T	Cest: ASTM D 4034/ACT	150
Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark		rel: 011-45-9630-3100 E ax: 011-45-9811-6125	xt:
EMARKS: None.			
ONCLUSION: Based on the above Results and Ac	cceptance Criteria,	the item tested:	
[x] Complies; [ ] Does not comply			
ERTIFICATION: I certify that the above resulith the procedures and equipment specified ab		ter testing specimens in	accordance
Phyllis Per	+ = = =		
UTHORIZED SIGNATURE NO	V 3 3 2018		
(Pa	age 2 of 2)		