

West Yorkshire Materials **Testing Service**

PO Box 5, Morley, LS27 0QP Nepshaw Lane South, Morley, Leeds Tel 0113 253 0241 Fax 0113 252 7029

Head of Laboratory G. Briggs C. Text ATI

Client:

Gabriel

Hjulmagervej 55 Postbox 59 DK-9100 Aalborg Denmark

Entry No:

45809-01

Date Received:

26th January 2011

Client's Description:

Sample of Fabric 8598 Event colours:-

60023, 60022, 66035, 64031, 66034, 66033, 60000, 64032, 63013

TEST REPORT

Tests Required:

Colour Fastness to Light and Rubbing

Date of Tests:

4.2.11 to 4.3.11

Light:

BS EN ISO 105: 1999 BO2 Method 2

The samples were exposed together with Standard References numbers 1-7. By comparison with the standard references the gradings were found to be as follows:-

60023:-	6-7	66033:-	5
60022:-	6-7	60000:-	6-7
66035:-	6-7	64032:-	6
64031:-	6-7	63013:-	7
66034:-	7		

Rubbing Fastness: BS EN ISO 105 - X12: 202


Staining			<u>Dry</u>	Wet
	60023:-	Warp Way Weft Way	4-5 4-5	4-5 4-5
	60022:-	Warp Way Weft Way	4-5 4-5	4-5 4-5
	66035:-	Warp Way Weft Way	4-5 4-5	4-5 4-5
	64031:-	Warp Way Weft Way	4-5 4-5	4-5 4-5

This is hereby certified to be a correct return of the tests made of the items referred to herein.

Head of Laboratory
17th March 2011

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

- for this Laboratory.
- * This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.







West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP Nepshaw Lane South, Morley, Leeds Tel 0113 253 0241 Fax 0113 252 7029

Head of Laboratory G. Briggs C. Text ATI

Client:

Gabriel

Hjulmagervej 55 Postbox 59 DK-9100 Aalborg

Denmark

Entry No:

45809-01

Staining			<u>Dry</u>	<u>Wet</u>			
<u>otaning</u>	66034:-	Warp Way Weft Way	4-5 4-5	4-5 4-5			
	66033:-	Warp Way Weft Way	4-5 4-5	4-5 4-5			
	60000:-	Warp Way Weft Way	5 5	5 5			
	64032:-	Warp Way Weft Way	4-5 4-5	4-5 4-5			
Chango ir	63013:-	Warp Way Weft Way	4-5 4-5	4-5 4-5			
Change ir	<u>i coloui</u>						
All Fabrics:-		Warp Way Weft Way	5 5	5 5			
Note: Change in colour is not a requirement of the method but was carried out at the request of the client.							

-----End of Document ------

This is hereby certified to be a correct return of the tests made of the items referred to herein.



G Briggs Head of Laboratory 17th March 2011

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

- * Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- * Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- * This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



