West Yorkshire Materials Testing Service
West Yorkshire Joint Services

West Yorkshire Materials Testing Service
PO Box 5, Nepshaw lane South, Morley,
Leeds LS27 0QP
Tel: 0113 253 0241 Fax: 0113 252 7029
Head of Laboratory: G. Briggs C. Text ATI

Client: Gabriel
Hjulmagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 56505-03

Date received: 29/01/2013

Client's Description: Sample of fabric Fighter 61095

TEST REPORT

Tests Required: Pilling, Colour Fastness to Rubbing in accordance with BS EN 14465

Date of Tests: 5.2.13 to 25.2.13

Conditioning: In accordance with BS EN ISO 139 : 2005 for a minimum of 24 hours at 65 +/- 4% Relative Humidity, 20 +/- 2ºC

Pilling: BS EN ISO 12945-2 : 2000
Load 415 g

After 2,000 rubs	5
After 5,000 rubs	5

Rubbing Fastness: BS EN ISO 105 – X12 : 2002

		Dry	Wet
Staining:-	Warp	4-5	4-5
	Weft	4-5	4-5
Change in colour:-	Warp	5	5
	Weft	5	5

Note: Change in colour is not a requirement of the method but was carried out at the request of the client.

----------End of Document----------

This is hereby certified to be a correct return of the tests made of the items referred to herein.

Geoff Briggs C.Text., A.T.I.
Head of Laboratory
8th March 2013

1104

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.