



# West Yorkshire Materials Testing Service

Page 1 of 2  
PO Box 5, Morley, LS27 0QP  
Nepshaw Lane South, Morley, Leeds  
Tel 0113 253 0241 Fax 0113 252 7029  
Head of Laboratory G. Briggs C. Text ATI

**Client:** Gabriel A/S  
Hjulmagervej 55  
Postbox 59  
DK-9100 Aalborg

**Entry No:** 24945-07

**Date Received:** 5<sup>th</sup> May 2004

**Client's Description:** 5 New Colours of Design Comfort:-  
61006 Brun ITC  
64006 Lys Red ITC  
64008 Red ITC  
66008 Mørk Bla ITC  
68005 Mørk Grøn IT

## TEST REPORT

**Test Required:** Colour Fastness to Rubbing

**Conditioning:** A minimum of 24 hours at 65 +/- 2% Relative Humidity, 20 +/- 2°C

**Method of Test:** BS EN ISO 105-X12: 2002

**Date of Test:** 10.5.03 to 13.5.03

The results are reported on the accompanying page. There are no results on this page.

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*

G Briggs  
Head of Laboratory  
27<sup>th</sup> May 2004



1104

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.


\* Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.

\* Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

\* This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



TRA09786



# West Yorkshire Materials Testing Service

Page 2 of 2  
PO Box 5, Morley, LS27 0QP  
Nepshaw Lane South, Morley, Leeds  
Tel 0113 253 0241 Fax 0113 252 7029  
Head of Laboratory G. Briggs C. Text ATI

Client: Gabriel A/S

Entry No. 24945-07

	<u>Dry</u>		<u>Wet</u>	
	<u>Warp Way</u>	<u>Weft Way</u>	<u>Warp Way</u>	<u>Weft Way</u>
61006				
Staining:-	4-5	4-5	4	4
Change in colour:-	5	5	5	5
64006				
Staining:-	4-5	4-5	4-5	4-5
Change in colour:-	5	5	5	5
64008				
Staining:-	4	4	4	4
Change in colour:-	5	5	5	5
66008				
Staining:-	4	4	3-4	4
Change in colour:-	5	5	5	5
68005				
Staining:-	4-5	4-5	4-5	4-5
Change in colour:-	5	5	5	5

**Note (i)** The grading of change in colour is not required by the test Method and was done only at the clients request.

**(ii)** The gradings were made by use of the Standard Geometric Grey Scales as specified in BS EN 20105 : 1993 AO2 and AO3 using the principles as specified in BS EN ISO 105 – AO1 : 1996.

----- End of Document -----

This is hereby certified to be a correct return of the tests made of the items referred to herein.

G Briggs  
Head of Laboratory  
27<sup>th</sup> May 2004



1104

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

\* Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.

\* Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

\* This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



TRA09786