

Test Report No. A 1001752-01-06**Testing of Flammability of Upholstery Fabric**Gregersensvej
P.O. Box 141
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19Client Gabriel A/S
Hjulmagervej 55, DK-9100 Aalborginfo@teknologisk.dk
www.teknologisk.dkMaterial Tested Cutting of an upholstery fabric as the enclosed sealed reference sample.
Weight: Approx. 275 g/m²
Fibre content (Manufacturers information):
88 % polyester, 12 % polyurethane.

Designation: 8430 COMFORT.



Sampling The material was submitted by the client and received at the Institute on 6 March 2002.

Test Method American standard Commercial Standard 191-53 (Revised) carried out as specified in California Bureau of Home Furnishings and Thermal Insulation Technical Bulletin 117, Section E.
A total of 20 determinations were made.

Testing Completed 11 March 2002

Test Results A test result of "no ignition" was recorded in each of the 20 tests.

Upholstery fabric 8430 COMFORT meets the requirements to flammability specified for upholstery fabrics in the above mentioned Bulletin 117, Section E, from Bureau of Home Furnishings and Thermal Insulation, State of California, USA.

*The test results relate only to the material tested.**This report cannot be reproduced in any way, except in full context, without approval in writing from Danish Technological Institute***Clothing and Textile**
Henrik Eigtved
Signatory
Anette Drøjdahl
Counter-signatory