

Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 66269

Date received: 28/07/2014

Client's Description: Sample of fabric Design 8807 Hush Colour 66133 D, Blue

TEST REPORT

Test Required: Flammability
Pre-treatment: None
Conditioning: A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C
Method of Test: BS EN 1021-1:2006 – smouldering cigarette
BS EN 1021-2:2006 – match flame equivalent
Date of Test: 04/08/2014

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

Note: A 35 kg/m³ CM foam (Carpenters RX36-125) was used as the filling.


The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



Geoff Briggs C. Text., A.T.I.
Head of laboratory
22nd August 2014



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 66269

During the tests the following data was recorded: -

	Smouldering cigarette		Match flame equivalent		
Time of Ignition (sec)	No Ignition	No Ignition	9	9	8
Time to extinction of flame after removal of butane flame (sec)	N/A	N/A	1	1	1
Time of Cover Split (sec)	Did not split	Did not split	Did not split	Did not split	Did not split
Melting (Yes or No)	No	No	No	No	No
Dripping (Yes or No)	No	No	No	No	No
Charring (Yes or No)	Yes	Yes	Yes	Yes	Yes

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



Geoff Briggs C. Text., A.T.I.
Head of laboratory
22nd August 2014



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

