West Yorkshire
Materials Testing Service
Nepshaw Lane South, Morley, Leeds, LS27 7JQ
Materials Testing Manager: D. J. Brockbank
t: 0113 393 9791
e: dale.brockbank@wyjs.org.uk
www.wyjs.org.uk/materialstesting

TEST REPORT

Client:	Gabriel Hjulmagervej 55 Postbox 59 DK-9100 Aalborg Denmark
Entry No:	74604-01
Date received:	19/04/2016
Client's Description:	11 samples of fabric Design: 2449 Go Couture, Colours: 61138, 63079, 61144, 62071, 60084, 61140, 60093, 60080, 61142, 61139 & 61141
Test Required:	Colour Fastness to Light & Colour Fastness to Rubbing
Date Tests Completed:	27/05/2016

Colour Fastness to Light: BS EN ISO 105-B02: 2013 Method 2

Specimens were exposed together with Standard References numbers 1-8. By comparison with the standard references the grading was found to be:

	BWS Rating
61138	**6-7**
63079	**7**
61144	**6-7**
62071	**7-8**
60084	**7-8**
61140	**7**
60093	**7**
60080	**6-7**
61142	**6**
61139	**6-7**
61141	**5-6**

----------End of Page----------

This is hereby certified to be a correct return of the tests made of the items referred to herein

Vivienne Brockbank
Senior Technician
06 June 2016

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- Tests marked [N] in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- Tests marked [F] in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
- Tests marked [S] in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

ilac-MRA UKAS TESTING 1104

West Yorkshire Materials Testing Service

Client: Gabriel

Entry No: 74604-01

Colour Fastness to Rubbing: BS EN ISO 105–X12:2002

Staining		Dry	Wet
61138	Warp Way	**5**	**5**
	Weft Way	**5**	**5**
63079	Warp Way	**4-5**	**4-5**
	Weft Way	**4-5**	**4-5**
62071	Warp Way	**5**	**4-5**
	Weft Way	**5**	**4-5**
60084	Warp Way	**5**	**4-5**
	Weft Way	**5**	**4-5**
61140	Warp Way	**5**	**5**
	Weft Way	**5**	**5**
60093	Warp Way	**5**	**5**
	Weft Way	**5**	**5**
60080	Warp Way	**5**	**5**
	Weft Way	**5**	**5**
61142	Warp Way	**5**	**4-5**
	Weft Way	**5**	**4-5**
61139	Warp Way	**5**	**4-5**
	Weft Way	**5**	**4-5**
61141	Warp Way	**4-5**	**4-5**
	Weft Way	**4-5**	**4-5**
Change in Colour		Dry	Wet
All colours	Warp Way	**5**	**5**
	Weft Way	**5**	**5**

Note: Change in colour is not a requirement of the method but was carried out at the request of the client.

----------End of Document----------