

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956

e-mail: testing@govmark.com

Page 1

Received: 06/12/2018 Completed: 06/26/2018 Letter:	O4 FF	P.O.#:	Test Report #:	3-26673-4-
Client's Style: Mica 2496 Content: 97% Post-Collentification # 60004 Light/Light Grey. End Use: Up		ed Polyester	, 3% Polyester. Finish: None. Wei	ght: 305 g/lm. Color
Tested For: Bente Ellingsoe, Quality Departmen Gabriel A/S	t	K	Key Test: AATCC 16 Lightfast/AC	CT 40Hrs 96
Hjulmagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100 Fax: 011-45-9811-6125	Ext:
192				
Test Category: Light Fastness Specifi PC: NS	er: ACT	NTR 9/15	LE 2015; V 08/15 dl/SM	
TEST PERFORMED: AATCC Test Method 16 - C	olorfastnes	s to Ligh	t:	
[] Option 1: Carbon Arc, Continuous [x] Option 3: Water Cooled Xenon Arc		nuous Lig	ht	
As cited by the ACT Voluntary Performa	nce Guideli	nes (Janu	ary 2015)	
Evaluated by comparison with AATCC Gra	y Scale for	Evaluati	ng Change in Color	
PRODUCT CATEGORY:	ACCEPTA	NCE CRITE	RIA:	
<pre>[x] Upholstery - Woven Fabrics [] Direct Glue Wallcoverings [] Wrapped Panels & Upholstered Walls [] Drapery</pre>	40 hour 40 hour	s - Grade s - Grade	4 minimum [CODE 96] 4 minimum [CODE 96] 4 minimum [CODE 96] 4 minimum [CODE 133]	
RESULTS:				
Number of Hours Rating				
40 Grade 4.5				
REMARKS: None.				
RATING SYSTEM:				
Grade 5 - No fading or color change Grade 4 - Slight fading or color chang Grade 3 - Noticeable fading or color c Grade 2 - Considerable fading or color Grade 1 - Excessive fading or color ch	hange change			
CONCLUSION: Based on the above Results a	nd Acceptan	ce Criter	ia, the item tested:	
[x] Complies; [] Does not comply				
CERTIFICATION: I certify that the above with the procedures and equipment specifi		e obtaine	d after testing specimens	in accordance
Phyl	lis Pettit		JUN 2 8 2018	
AUTHONIZED SIGNATURE SGS GOVMARK			JUN 2 O ZOIO	
/FF/jb /pm	(Page 1 o	f 1)		