

Received: 10/26/2018 **Completed:** 11/07/2018 **Letter:** B **RV** **P.O.#:** **Test Report #:** 3-29298-0-

Client's Identification Style: Event. Content: 100% Polyester. Finish: None. Weight: 420 g/lm. Color: 60999 Black. Product End Use: Upholstery.

Tested For: **Bente Ellingsoe, Quality Department** **Key Test:** ASTM D 5034/ACT 140
 Gabriel A/S
 Hjulmagervej 55 **Tel:** 011-45-9630-3100 **Ext:**
 DK-9000 Aalborg, Denmark **Fax:** 011-45-9811-6125

Test Category: Tensile Specifier: ACT LE 2015; V 08/15 PC: 8H dl/SM
 NTR 9/15

TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile Fabrics (Grab Test) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

| | |
|---|--|
| PRODUCT CATEGORY: | ACCEPTANCE CRITERIA (for warp and weft): |
| ----- | ----- |
| <input checked="" type="checkbox"/> Upholstery | 50 lbs. minimum average |
| <input type="checkbox"/> Wrapped Panels & Upholstered Walls | 35 lbs. minimum average |
| <input type="checkbox"/> Draperies | No requirement |

RESULTS:

| Direction | Specimen # | (lbs) |
|-----------|------------|-------|
| ----- | ----- | ----- |
| Warp: | 1 | 342 |
| | 2 | 345 |
| | 3 | 345 |
| | 4 | 363 |
| | 5 | 322 |
| | Avg: | 343 |
| Weft: | 1 | 262 |
| | 2 | 274 |
| | 3 | 287 |
| | 4 | 125 |
| | 5 | 303 |
| | 6 | 281 |
| | 7 | 269 |
| | 8 | 293 |
| | Avg: | 262 |


REMARKS: None.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply; Does not apply to drapery fabrics

| | | | | | |
|--|---|------------------|-----------|--|----------------------------------|
| Received: 10/26/2018 | Completed: 11/07/2018 | Letter: B | RV | P.O.#: | Test Report #: 3-29298-0- |
| Client's Identification | Style: Event. Content: 100% Polyester. Finish: None. Weight: 420 g/lm. Color: 60999 Black. Product End Use: Upholstery. | | | | |
| Tested For: Bente Ellingsoe, Quality Department | | | | Key Test: ASTM D 5034/ACT | 140 |
| Gabriel A/S Hjulgagervej 55 DK-9000 Aalborg, Denmark | | | | Tel: 011-45-9630-3100 Fax: 011-45-9811-6125 | Ext: |

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



 AUTHORIZED SIGNATURE
 SGS GOVMARK
 /jab
 /pm

Phyllis Pettit

NOV 15 2018
 (Page 2 of 2)