

Nepshaw Lane South, Morley, Leeds, LS277JQ Materials Testing Manager: D. J. Brockbank

t: 0113 393 9791

e: dale.brockbank@wyjs.org.uk www.wyjs.org.uk/materialstesting



TEST REPORT

Client: Gabriel

> Hjulmagervej 55 Postbox 59 DK-9100 Aalborg

Denmark

96485-01 **Entry No:** 27/02/2018 Date received:

Client's Description: 11 samples of fabric: Mood, Colours: 01105, 01106, 02105, 02106, 02107, 03105,

04104, 04105, 04106, 05105 & 08101

Test Required: Colour Fastness to Light

Date Tests Completed: 11/04/2018

Colour Fastness to Light: BS EN ISO 105-B02: 2014 Method 2

Specimens were exposed together with Standard References numbers 1-8. By comparison with the standard references the grading was found to be:

	BWS Rating
01105	6
01106	6-7
02105	6
02106	6-7
02107	5-6
03105	6
04104	5
04105	7
04106	6-7
05105	7
08101	7

This is hereby certified to be a correct return of the tests made of the items referred to herein

Vivienne Brockbank

Technician 13 April 2018

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

- Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory. Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation. Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.

- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

 Uncertainty budgets for test methods contained within this report are available on request. This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



