



DANISH
TECHNOLOGICAL
INSTITUTE

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Test Report

Report No.: A 895284-2

Assignor: Gabriel A/S- Designmaster
Hjulgagervej 55
9000 Aalborg

Page 1 of 2
Initials: Chf/Ieln
Order no.: 895284
No. of appendix: 1

Subject: Combination of upholstered material tested:
Cover: Sample of upholstery fabric, designated: 2509 Rondo, colour: 68225 (as per info from the assigner)
Approximate mass per area unit: 338 g/m²

Filling: CMHR foam designated, CH4038. (as per info from the assigner)
Approximate density: 50 kg/m³.

Sampling: The material for testing was submitted by the assigner and received on Danish Technological Institute 30 October 2019.

Method: Testing of ignitability according to EN 1021-2:2014, Furniture - Assessment of ignitability of upholstered furniture - Part 2: Ignition source match flame equivalent.

Details of the test are given on page 2 in this report.

Period: The testing was completed 31 October 2019.

Result: According to the criteria of ignition described in EN 1021-2, chapter 3, the result is:

Non-ignition > PASS

Storage: The test material will be destroyed after 3 months, unless otherwise agreed.

Terms: The accredited test was carried out according to DANAK's general conditions see www.danak.dk and according to the General Terms and Conditions regarding Commissioned Work Accepted by the Danish Technological Institute, which apply at the time of signing the agreement. The test is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

Date/place: 31 October 2019, Danish Technological Institute, Textile, Taastrup

Signature: Test responsible

Co-signatory



Report no.: A 895284-2
Page: 2 of 2
Initials: Chf/leln

**Results,
continued:**

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Test method: EN 1021-2:2014.

Ignition source: Match flame equivalent.

Conditioning atmosphere: 23±2 °C / 50±5 % RH.

Test result: Non-ignition > PASS

Smouldering criteria	Match Flame equivalent		
	Test 1	Test 2	Test 3
Unsafe escalating combustion (3.1.a)	No	No	No
Test assembly largely consumed (3.1.b)	No	No	No
Smoulders to extremities (3.1.c)	No	No	No
Smoulders through thickness (3.1.c)	No	No	No
Smoulders more than 1 hour (3.1.d)	No	No	No
Progressive smouldering on final examination (3.1.e)	No	No	No
Flaming criteria			
Unsafe escalating combustion (3.2.a)	No	No	No
Test assembly essentially consumed (3.2.b)	No	No	No
Flames to extremities, except upper margins (3.2.c)	No	No	No
Flames through thickness (3.2.c)	No	No	No
Flames longer than 120 sec. (3.2.d)	No	No	No

Comments:

Before testing the sample was **not** subjected to the water soaking and drying procedure described in EN 1021-2, annex D.

Report no.: A 895284-2
Appendix: 1
Page: 1 of 1
Initials: Chf/leln

