

Received: 11/25/2019 Completed: 12/03/2019 Letter: V4 RV P.O.#: Test Report #: 3-35831-4-

Client's Identification Style: Connect. Content: 48% Wool, 41% Rec PE, 9% PA, 2% PE. Weight: 377 g/lm. Color: 60147 Light Gray. Product End Use: Upholstery.

Tested For: Bente Ellingsoe, Quality Department Key Test: ASTM D 5034/ACT 165
 Gabriel A/S
 Hjulmagervej 55 Tel: 011-45-9630-3100 Ext:
 DK-9000 Aalborg, Denmark Fax: 011-45-9811-6125

Test Category: Tensile Specifier: ACT LE 2018; V 01/19 PC: 8H dl/SM
 NTR 9/15

TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile Fabrics (Grab Test) --

As cited by the ACT Voluntary Performance Guidelines (August 2018)

PRODUCT CATEGORY: ACCEPTANCE CRITERIA (for warp and weft):

 Upholstery 50 lbs. minimum average
 Wrapped Panels & Upholstered Walls 35 lbs. minimum average
 Draperies No requirement

RESULTS:

Direction	Specimen #	(lbs)
Warp:	1	169
	2	175
	3	179
	4	195
	5	173
	Avg:	178
Weft:	1	216
	2	207
	3	206
	4	204
	5	216
	6	219
	7	209
	8	204
	Avg:	210


REMARKS: None.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply; Does not apply to drapery fabrics

Received: 11/25/2019	Completed: 12/03/2019	Letter: V4	RV	P.O.#:	Test Report #: 3-35831-4-
Client's Identification	Style: Connect. Content: 48% Wool, 41% Rec PE, 9% PA, 2% PE. Weight: 377 g/lm. Color: 60147 Light Gray. Product End Use: Upholstery.				
Tested For: Bente Ellingsoe, Quality Department				Key Test: ASTM D 5034/ACT	165
Gabriel A/S Hjulgagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100	Ext:	
			Fax: 011-45-9811-6125		

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



 AUTHORIZED SIGNATURE
 SGS GOVMARK
 /ab /pm

Phyllis Pettit

DEC 26 2019

(Page 2 of 2)