

Received: 11/20/2019 Completed: 01/07/2020 Letter: L FF P.O.#: Test Report #: 3-35682-0-RV

**Client's Identification** Style: Swing. Content: 54% New Zealand Wool, 44% Polyester, 2% Polyamide. Weight: 430 g/lm. Color: 51404 Light Grey. Product End Use: Upholstery.

**Tested For: Bente Ellingsoe, Quality Department** **Key Test: AATCC 16 Lightfast/ACT 40Hrs**  
 Gabriel A/S RVNC  
 Hjulmagervej 55 **Tel: 011-45-9630-3100 Ext:**  
 DK-9000 Aalborg, Denmark **Fax: 011-45-9811-6125**

Test Category: Light Fastness Specifier: ACT NTR 9/15 LE 2018; V 01/19  
 PC: NS dl/SM

TEST PERFORMED: AATCC Test Method 16 - Colorfastness to Light:

- Option 1: Carbon Arc, Continuous Light
- Option 3: Water Cooled Xenon Arc Lamp, Continuous Light

As cited by the ACT Voluntary Performance Guidelines (August 2018)

Evaluated by comparison with AATCC Gray Scale for Evaluating Change in Color

PRODUCT CATEGORY:	ACCEPTANCE CRITERIA:
<input checked="" type="checkbox"/> Upholstery - Woven Fabrics	40 hours - Grade 4 minimum [CODE 115]
<input type="checkbox"/> Direct Glue Wallcoverings	40 hours - Grade 4 minimum [CODE 115]
<input type="checkbox"/> Wrapped Panels & Upholstered Walls	40 hours - Grade 4 minimum [CODE 115]
<input type="checkbox"/> Drapery	60 hours - Grade 4 minimum [CODE 155]

RESULTS:

Number of Hours	Rating
40	Grade 4.5

REMARKS: None.


RATING SYSTEM:

- Grade 5 - No fading or color change
- Grade 4 - Slight fading or color change
- Grade 3 - Noticeable fading or color change
- Grade 2 - Considerable fading or color change
- Grade 1 - Excessive fading or color change

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies;  Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

  
 AUTHORIZED SIGNATURE Phyllis Pettit RV.01.10.20 /gb  
 SGS GOVMARK **JAN 13 2020**  
 FF/ab (Page 1 of 1)