



Wira House, West Park Ring Road,
Leeds, LS16 6QL, UK.
Telephone: +44 (0)113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 27 January 2021

Our Ref: 23/58122-16
Your Ref: 0011512406

Page: 1 of 4

Client: Gabriel A/S
Hjulgagervej 55
DK-9000 Aalborg
Denmark

Job Title: BS EN 1021 Part 1

Client's Order No: 0011512406

Date of Receipt: 04 January 2021
Date of Test Start: 18 January 2021

Description of Sample(s): One sample of fabric identified as follows was received for testing:

Omega 60999 / Black

Work Requested: We were asked to make the following test:

BS EN 1021-1:2014



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Gabriel A/S

Sample was identified as follows:

Omega 60999 / Black

Wira House, West Park Ring Road,
Leeds, LS16 6QL, UK.
Telephone: +44 (0)113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 27 January 2021

Our Ref: 23/58122-16
Your Ref: 0011512406

Page: 2 of 4

FIRE TESTS ACCORDING TO BS EN 1021-1:2014

Assessment of the ignitability of upholstered furniture. Part I. Ignition Source 0: Smouldering cigarette

Pre-Treatment

The sample did not have a flame retardant treatment therefore it was not subjected to a water soak pre-treatment

Conditioning

The sample was conditioned for at least 16 hours at a temperature of $23\pm 2^{\circ}\text{C}$ and relative humidity of $50\pm 5\%$.

The sample was tested in a room of volume 25m^3 and 18°C .

Procedure

The test was carried out in accordance with BS EN 1021-1:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately $20\text{-}22\text{ kg/m}^3$.

Tests were made using ignition source 0.

Requirements

The specimens shall not:-

Smouldering Criteria

- display escalating combustion requiring active extinction.
- smoulder or burn until it is essentially consumed within the test duration.
- smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- smoulder for more than one hour.
- on final examination, show evidence of progressive smouldering.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road,
Leeds, LS16 6QL, UK.
Telephone: +44 (0)113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 27 January 2021

Our Ref: 23/58122-16
Your Ref: 0011512406

Page: 3 of 4

Gabriel A/S

Requirements (continued)

Flaming Criteria

- a) show evidence of flaming initiated by a smouldering source.

Results

| | Cigarette | | | Comments |
|---|-----------|----|----------------|----------|
| | 1 | 2 | 3 ¹ | |
| Smouldering Criteria (Yes/No) | | | | |
| Unsafe escalating combustion | No | No | | |
| Test assembly consumed | No | No | | |
| Smoulders to extremities | No | No | | |
| Smoulders through thickness | No | No | | |
| Smoulders more than 1 hour | No | No | | |
| In final examination, presence of progressive smouldering | No | No | | |
| Ignitability Performance (Yes/No) | | | | |
| Occurrence of flames | No | No | | |
| Ignition / Non Ignition (I/NI) | NI | NI | | |

¹ Results for cigarette 3, only if applicable.

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.





TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road,
Leeds, LS16 6QL, UK.
Telephone: +44 (0)113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 27 January 2021

Our Ref: 23/58122-16
Your Ref: 0011512406

Page: 4 of 4

Gabriel A/S

Comments

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-1.

This report relates only to the samples submitted and as described in the report.

The overall uncertainty budget for BS EN 1021: Part 1:2014 is as follows:-

Timings: ± 2 seconds.

Reported by:.....
B Bland
Laboratory Technician

Countersigned By:.....
P Doherty
Manager

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.