TÜVRheinland®
Precisely Right.

Gabriel

Softlines

Test Report	**No. 28511289**	**Date: 15th February 2021**	**Page 1 of 2**

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description	**:**	Nemo
Customer	**:**	**Gabriel**
Colour	**:**	60999
Product type	**:**	Upholstery fabric
Fiber content	**:**	-

Test Performed : Selected test(s) as requested by applicant
* * * * *
Sample Receiving Date : 11th January 2021
Testing Period : 11th January 2021 – 15th February 2021
Test Result(s) : For further details, please refer to the following page(s).

Conclusion:

Test Property	Remarks
Pilling	-
Abrasion	-

Signed for and on behalf of
TÜV Rheinland UK LTD

George Mehmet
2021.02.11 08:45:50 Z

George Mehmet
Laboratory Technician

UKAS TESTING
8400

Test result is drawn according to the kind and extent of tests performed.
Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.

Results:

Pilling Resistance
(BS EN ISO 12945-2:2000; Martindale Abrasion & Pilling Tester; Total Load Applied 415g, tested against wool abradent fabric)
No cleansing required

Sample	Average Result
After 2000 Rubs Rating	5
After 5000 Rubs Rating	5

Remarks: Pilling Rating
5 - No change
4 - Slight surface fuzzing and/or partially formed pills
3 - Moderate surface fuzzing and/or moderate pilling. Pills of varying size and density partially covering the specimen
2 - Distinct fuzzing and/or distinct pilling. Pills of varying size and density covering a large proportion of the specimen surface
1 - Dense surface and/or severe pilling. Pills of varying size and density covering the whole of the specimen surface

Abrasion Resistance
(BS EN ISO 12947-2:2016/AC:2006 according to BS EN 14465); Martindale Wear & Abrasion Tester; 12 kPa Pressure)

	Result		
	Specimen 1	**Specimen 2**	**Specimen 3**
End point reached, No three thread breakdown	50,000	50,000	50,000
Overall result	50,000		
Colour Change At 3000 (rubs)	5	5	5

Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good
Observation Technique:40 fold magnification

-End of Test Report-