

Softlines

Test Report	No. 28511164 – Amended 1	Date: 17th November 2020	Page 1 of 2
--------------------	---------------------------------	--	--------------------

The following sample(s) was/were submitted and identified on behalf of the client as:


Sample Description	:	Focus Col: D.Blue 66010
Customer	:	Gabriel
Product type	:	Upholstery fabric
Content Fiber	:	100% Wool

Test Performed : Selected test(s) as requested by applicant
 * * * * *
 Sample Receiving Date : 6th November 2020
 Testing Period : 6th November 2020 – 17th November 2020 This A1 report issued
 19/3/2021 supersedes report issued 17/11/2020. Amended style,
 colour, and fibre composition. Pilling results omitted.
 Test Result(s) : For further details, please refer to the following page(s).

Conclusion:

Test Property	Remarks
Abrasion	-

Signed for and on behalf of
TÜV Rheinland UK LTD


George Mehmet
2021.03.19
11:07:14 Z

George Mehmet
Laboratory Technician



8400

*Test result is drawn according to the kind and extent of tests performed.
 Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety
 mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*

Test Report	No. 28511164 – Amended 1	Date: 17th November 2020	Page 2 of 2
--------------------	---------------------------------	--	--------------------

Results:

Abrasion Resistance (BS EN ISO 12947-2:2016/AC:2006 according to BS EN 14465); Martindale Wear & Abrasion Tester; 12 kPa Pressure)			
Result			
	Specimen 1	Specimen 2	Specimen 3
Specimens removed at stepwise intervals	10,000	20,000	30,000
	Specimen 4	Specimen 5	
Specimens removed at stepwise intervals	40,000	50,000	
	Specimen 1	Specimen 2	Specimen 3
End point reached, three thread breakdown	100,000	100,000	100,000
Overall Result	100.000		
Colour Change At 3000 (rubs)	5	5	5
Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good Observation Technique:40 fold magnification			

-End of Test Report-