

Nepshaw Lane South, Morley, Leeds, LS27 7JQ Materials Testing Manager: D. J. Brockbank

t: 0113 393 9791

e: dale.brockbank@wyjs.org.uk www.wyjs.org.uk/materialstesting



TEST REPORT

Client: Gabriel

> Hjulmagervej 55 Postbox 59 DK-9100 Aalborg

Denmark

93245 **Entry No:**

Date received: 06/12/2017

Client's Description: Sample of fabric: 2477 Felicity, Colour: 62080

Test Required: Abrasion and Pilling in accordance with BS EN 14465. Colour Fastness to

Rubbing and Colour Fastness to Light

Conditioning: In accordance with BS EN ISO 139: 2005 for a minimum of 24 hours at

65+/-4%, Relative Humidity, 20+/-2°C

Date Tests Completed: 08/01/2018

Abrasion Resistance: BS EN ISO 12947-2: 1988 / AC 2008 according to BS EN 14465: 2003

The tests were carried out using a pressure of 12 +/- 0.3 kPa The criterion for judging end point was three threads broken

> Specimen 1 110,000 rubs Specimen 2 110,000 rubs Specimen 3 100,000 rubs Specimen 4 90,000 rubs **Overall Result** 90,000 rubs

Change in colour after 3,000 rubs: 4

Observation Technique: 10 fold magnification

Type of Fabric: Flat Woven

Note: Pilling occurred during testing and when observed pills were cut off at observation interval.

This is hereby certified to be a correct return of the tests made of the items referred to herein

Vivienne Brockbank

Technician

08 January 2018

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

- Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory. Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation. Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.







Client: Gabriel

Entry No: 93245



Pilling: BS EN ISO 12945-2: 2000 Load 415g

	Rating
After 2,000 rubs	5
After 5,000 rubs	5

Colour Fastness to Rubbing: BS EN ISO 105-X12: 2016F

<u>Staining</u>		Dry	Wet
_	Warp Way	5	5
	Weft Way	5	5
Change in Colour	·	Dry	Wet
	Warp Way	5	5
	Weft Way	5	5

Note: Change in colour is not a requirement of the method but was carried out at the request of the client.

Colour Fastness to Light: BS EN ISO 105-B02: 2014 Method 2

A specimen was exposed together with Standard References numbers 1-8. By comparison with the standard references the grading was found to be:

BWS Rating 6-7

-----End of Document------