

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 email: govmark.accounting@sgs.com

Page 1

		,		1 450 1
Received: 11/16/2018 Completed: 12/05/2018 Letter	r: R2 FF	P.O.#:	Test Report #:	3-29650-2-
Client's Style: Runner. Content: 100% Polyest Identification	er. Weight: 510	g/lm. Color: 6	8109 Green. Product End Use: Up	pholstery.
Tested For: Bente Ellingsoe, Quality Departme	ent	Ke	y Test: AATCC 16 Lightfast/AC	CT 40Hrs 96
Gabriel A/S			TR. 1. 011 45 0520 0100	T
Hjulmagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100 Fax: 011-45-9811-6125	Ext:
211 your Amoorg, Dominan			Tux. 011 43 7011 0123	
Test Category: Light Fastness Specif PC: NS	Eier: ACT	NTR 9/15	LE 2015; V 08/15 dl/SM	
TEST PERFORMED: AATCC Test Method 16 -	Colorfastne	ss to Light	:	
[] Option 1: Carbon Arc, Continuous [x] Option 3: Water Cooled Xenon Arc		inuous Ligh	t	
As cited by the ACT Voluntary Perform	mance Guidel	ines (Janua	ry 2015)	
Evaluated by comparison with AATCC Gr	ray Scale fo	r Evaluatin	g Change in Color	
PRODUCT CATEGORY:	ACCEPT	ANCE CRITER	IA:	
<pre>[x] Upholstery - Woven Fabrics [] Direct Glue Wallcoverings [] Wrapped Panels & Upholstered Wall [] Drapery</pre>	40 hou Ls 40 hou	rs - Grade rs - Grade rs - Grade rs - Grade	4 minimum [CODE 96] 4 minimum [CODE 96]	
RESULTS:				
Number of Hours Rating				
40 Grade 4				
REMARKS: None.				•
RATING SYSTEM:				
Grade 5 - No fading or color change Grade 4 - Slight fading or color char Grade 3 - Noticeable fading or color Grade 2 - Considerable fading or color Grade 1 - Excessive fading or color of	change or change			
CONCLUSION: Based on the above Results	and Accepta	nce Criteri	a, the item tested:	
[x] Complies; [] Does not comply				
CERTIFICATION: I certify that the above with the procedures and equipment specif	e results we lied above.	re obtained	after testing specimens	in accordance
Phr	yllis Pettit			
AVARCEZED SIGNATURE		JAN 0 7	2019	
SGS GOVMARK				
FF /gb	(Page 1 of	1)		