

For the Account of:

Gabriel A/S Hjulmagervej 55 9000 Aalborg Denmark

Client's Identification:

Swing COL 51404

CERTIFICATE OF TESTING

CERT #3193.01

TEST PERFORMED: Pilling Resistance and Other Related Surface Changes of Textile Fabrics : Martindale Tester ASTM D4970/D4970M-16e2

TEST RESULTS

Specimen	Rating 1.5 in	Rating 5.5 in	
1	4.0	5.0	
2	4.0	5.0	
3	4.0	5.0	
4	4.0	5.0	
Average	4.0	5.0	Overall Average: 4.5

RATING SYSTEM

Class 5.0	No Pilling
Class 4.0	Slight Pilling
Class 3.0	Moderate Pilling
Class 2.0	Severe Pilling
Class 1.0	Very Severe Pilling

NOTES

Test Conditions:	70 ±4°F, 65 ±5% Relative Humidity
Sampling Method:	As Received
Viewing Apparatus:	SpectraLight QC Lightbooth
Viewing Option:	45 degree
Rating Standard:	ADJD3512 Photographic Standards
Running Times:	1000 movements

Criteria

ACCEPTANCE CRITERIA

A.C.T. Standard:	Acceptance Crite
Upholstery	Class 3 minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

ata Stiver

Authorized Signature

Date Order Completed: 12/02/2021

Date of Issue: 1/10/2022

Report Number: 21-006184 **Revision Number:2**

Date Order Received: 11/30/2021

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples as received under the predetermined and specific test conditions prescribed by the standard specific at a conditions prescribed by the standard specificate applies only to the standards or processing identified and to the random sample(s) tested. This certificate of the piece or lot only to the standards or processing identified and to the random sample(s) tested.