



For the Account of: Gabriel A/S
 Hjulmagervej 55
 9000 Aalborg Denmark

Client's Identification: NOBEL COL. 61290

CERTIFICATE OF TESTING

TEST PERFORMED: Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D4034-92

TEST RESULTS

Specimen	Warp Yarn Slippage (lbf)	Type of Failure	Specimen	Fill Yarn Slippage (lbf)	Type of Failure
1	22.9	SS	1	22.1	SS
2	29.0	SS	2	28.3	SS
3	24.6	SS	3	23.1	SS
4	26.5	SS	4	32.9	SS
5	26.8	SS	5	34.1	SS
Avg. Warp	26.0		Avg. Fill	28.0	

ABBREVIATIONS USED

- SB** Seam broke before 1/4" slippage - Results should reflect this
- SS** 1/4" slippage occurred - Note: Actual slippage of yarns is visible
- FB** Fabric broke before 1/4" slippage - Note: Actual breakage is visible

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Seam Description:

Seam Type	Standard Lockstitch
Stitches per Inch	7 ± 0.5 stitches per inch
Needle Used	Size 22 NM: 140, 135x17 ball point needle
Thread	Nymo EX Bonded Nylon thread; 5x is used for the bobbin and 8x is used for the needle

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
Upholstery	25 lbs. Minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 05/24/2023