



Received: 07/22/2016 Completed: 07/28/2016 Letter: O4 RV P.O.#: Test Report #: 3-14513-4-

Client's Identification Style: Rhythm. Composition: 100% Polyester/Polyester Fire Retardant. Weight: 526 g/lm. Product End Use: Upholstery.

Tested For: Bente Ellingsoe, Quality Department Key Test: ASTM D 5034/ACT 140  
 Gabriel A/S  
 Hjulmagervej 55 Tel: 011-45-9630-3100 Ext:  
 DK-9000 Aalborg, Denmark Fax: 011-45-9811-6125

Test Category: Tensile Specifier: ACT LE 2015; V 08/15 PC: 8H dl/SM  
 NTR 9/15

TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile  
 Fabrics (Grab Test) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY:	ACCEPTANCE CRITERIA (for warp and weft):
-----	-----
[x] Upholstery	50 lbs. minimum average
[ ] Wrapped Panels & Upholstered Walls	35 lbs. minimum average
[ ] Draperies	No requirement

RESULTS:

Direction	Specimen #	(lbs)
-----	-----	-----
Warp:	1	174
	2	150
	3	153
	4	175
	5	173
	Avg:	165
Weft:	1	118
	2	110
	3	116
	4	111
	5	119
	6	114
	7	117
	8	118
	Avg:	115

REMARKS: None.


CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [ ] Does not comply; [ ] Does not apply to drapery fabrics



Received: 07/22/2016	Completed: 07/28/2016	Letter: O4	RV	P.O.#:	Test Report #:	3-14513-4-
Client's Identification	Style: Rhythm. Composition: 100% Polyester/Polyester Fire Retardant. Weight: 526 g/lm. Product End Use: Upholstery.					
Tested For: Bente Ellingsoe, Quality Department			Key Test: ASTM D 5034/ACT		140	
Gabriel A/S Hjulgagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100 Fax: 011-45-9811-6125		Ext:	

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

  
 -----  
 AUTHORIZED SIGNATURE  
 GOVMARK  
 /pm /mo

*Ms. Phyllis Pettit*

AUG 1 0 2016

(Page 2 of 2)