



Received:07/11/2016	Completed:08/19/2016	Letter: A	RV	P.O.#:	Test Report #:	3-14262-0-
Client's Identification	Style: Breeze Fusion. Composition: 88%/12% Wool/Pa. Weight: 590 g/lm.					
Tested For: Bente Ellingsoe, Quality Department			Key Test: ASTM D 4966/ACT SP 130K		450	
Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100 Fax: 011-45-9811-6125		Ext:	

LE: 2012e1 V 03/15

CODE: 200,000 RQ /jd

TEST PERFORMED: ASTM D 4966 Martindale Abrasion Method Standard Test Method for Abrasion Resistance of Textile Fabrics (Upholstery Fabric Classification)

Abradant: Plain weave cross-bred worsted wool standard fabric, 5.8 oz/sq yd  
 Pressure: 1.74 psi ± 0.04 psi (12 kPa)

Foam disk is inserted if test item is less than 14.7 oz/yd<sup>2</sup>.

APPROXIMATE FABRIC WEIGHT (as measured by Govmark): 12.6 oz/yd<sup>2</sup>

INTERPRETATIVE OPTIONS:

Option 1: Smooth or Textured Surface Fabrics --

Woven Fabric: The end point (wear) is reached when two or more threads have broken; loss of special effect yarn or pile exposing base fabric.

Knitted Fabric: The end point is reached when a hole appears.

Option 2: Slightly Napped, Brushed, Sueded Fabrics --

The end point (wear) is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain. The shade end point (wear) is reached when a color change is assigned a Grey Scale rating of 3 or less.

RATING SYSTEM FOR OPTION 1:

- 5 - None or negligible change in appearance
- 4 - Slight change in appearance
- 3 - Moderate change in appearance
- 2 - Objectionable change in appearance (broken yarns, floating yarns, loss of pile, core yarn exposed, a hole, etc.)
- 1 - Severe change in appearance (complete fabric break, base fabric exposed, or running and pulling of knit)

RATING SYSTEM FOR OPTION 2: (AATCC Grey scale for Color Change)

- Grade 5 - No color change
- Grade 4 - Slight color change
- Grade 3 - Noticeable color change
- Grade 2 - Considerable color change
- Grade 1 - Excessive color change



Received:07/11/2016	Completed:08/19/2016	Letter: A	RV	P.O.#:	Test Report #:	3-14262-0-
Client's Identification	Style: Breeze Fusion. Composition: 88%/12% Wool/Pa. Weight: 590 g/lm.					
Tested For: Bente Ellingsoe, Quality Department			Key Test: ASTM D 4966/ACT SP 130K			450
Gabriel A/S Hjulgagervej 55 DK-9000 Aalborg, Denmark			Tel: 011-45-9630-3100			Ext:
			Fax: 011-45-9811-6125			

RESULTS: Visual evaluation (see page 1 for Rating System)

No. of Rubs	Rating
5,000	4.5
10,000	4.5
20,000	4.5
30,000	4
40,000	4
50,000	3.5
60,000	3.5
70,000	3.5
80,000	3.5
90,000	3.5
100,000	3.5
110,000	3
115,000	3
120,000	3
125,000	3
130,000	2.5
	Broken yarns

NOTE: For tests exceeding 50,000 rubs, the abradant fabric is changed at 50,000 rubs if breakdwon has not been reached.



Received:07/11/2016 Completed:08/19/2016 Letter: A RV P.O.#: Test Report #: 3-14262-0-

Client's Identification Style: Breeze Fusion. Composition: 88%/12% Wool/Pa. Weight: 590 g/lm.

Tested For: Bente Ellingsoe, Quality Department Key Test: ASTM D 4966/ACT SP 130K 450  
 Gabriel A/S  
 Hjulmagervej 55 Tel: 011-45-9630-3100 Ext:  
 DK-9000 Aalborg, Denmark Fax: 011-45-9811-6125

End Point Evaluation:

Specimen #	Number of Rubs End Point
1	130,000
2	130,000
3	130,000
AVG:	130,000

REMARKS: None.


ACCEPTANCE CRITERIA: As cited by ACT Voluntary Performance Guidelines (January 2005) For Upholstery Materials --

General Contract Upholstery: No objectionable change in appearance at 20,000 rubs  
 Heavy Duty Upholstery: No objectionable change in appearance at 40,000 rubs

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested is rated for:

General Contract Upholstery;  Heavy Duty Upholstery;  Unrated

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

  
 -----  
 AUTHORIZED SIGNATURE  
 GOVMARK  
 /pm/mo

AUG 29 2016

Ms. Phyllis Pettit