West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Client:	Gabriel A/S Hjumagervej 55 Postbox 59 DK-1900 Aalborg Denmark
Entry No:	51671
Date Received:	26/7/12
Client's Description:	2 fabric samples : Dragon col. 60123 & Dragon col. 67041

TEST REPORT

Tests Required:	Colour fastness to light and rubbing
Date of Test:	27/7/12 to 29/8/12
Method of Test :	BS EN ISO 105 : 1999 BO2 Method 2

The samples were exposed together with Standard Reference numbers 1 – 7. By comparison with the standard references the gradings were found to be as follows:-

60123 : - 5
67041 : - 5

Rubbing : BS EN ISO 105 – X12: 2002

	Dry	Wet
Staining :- 60123 :- length way	4-5	4-5
width way	4-5	4-5
67041 :- length way	4-5	4-5
Width way	4-5	4-5
Change in colour :- both fabrics :- length way	5	5
width way	5	5

Note :- Change in colour is not a requirement of the method but was carried out at the request of the client.

---------- End of Document ----------

This is hereby certified to be a correct return of the tests made of the items referred to herein.

G Briggs
Head of Laboratory
31st August 2012

1104

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.