

Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 56505-01

Date received: 29/01/2013

Client's Description: Sample of fabric Fighter 61095

TEST REPORT

Test Required: Flammability
Pre-treatment: None
Conditioning: A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C
Method of Test: BS EN 1021-1:2006 – smouldering cigarette
BS EN 1021-2:2006 – match flame equivalent
Date of Test: 08/02/2013

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	Flaming ceased within the specified two minute period after removal of the butane and no progressive smouldering occurred.	PASS

Note: A 35 kg/m³ CMHR foam (Carpenters RX36-125) was used as the filling


The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



Geoff Briggs C. Text., A.T.I.
Head of Laboratory
26th February 2013



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 56505-01

During the tests the following data was recorded: -

Time of Ignition (sec)	Smouldering cigarette		Match flame equivalent		
	No Ignition	No Ignition	5	5	5
Time to extinction of flame after removal of butane flame (sec)	N/A	N/A	1	1	1
Time of Cover Split (sec)	25	28	5	5	5
Melting (Yes or No)	Yes	Yes	Yes	Yes	Yes
Dripping (Yes or No)	No	No	No	No	No
Charring (Yes or No)	Yes	Yes	Yes	Yes	Yes

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



Geoff Briggs C. Text., A.T.I.
Head of Laboratory
26th February 2013



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

