



Received:01/03/2017 Completed:01/05/2017 Letter: K TM P.O.#: Test Report #: 3-17055-0-

Client's Identification | Style: Step. Composition: 100% Trevira CS. Weight: 470 g/lm. Product End Use: Upholstery. Color: Grey

Tested For: **Bente Ellingsoe, Quality Department** Key Test: ASTM D 3511/ACT 140
 Gabriel A/S
 Hjulmagervej 55 Tel: 011-45-9630-3100 Ext:
 DK-9000 Aalborg, Denmark Fax: 011-45-9811-6125

Test Category: Brush Pilling Specifier: ACT LE 2015; V 08/15 PC: 4H dl/SM
 NTR 7/16

TEST PERFORMED: ASTM D 3511 - Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textiles Fabrics: Brush Pilling Tester Method (LE 2013; V 3/15) --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: Upholstery - Woven Fabrics

ACCEPTANCE CRITERIA: Class 3 Minimum Average

RESULTS:

Specimen #	Rating
1	Class 4.5
2	Class 4.5
3	Class 4.5
Avg:	Class 4.5

OBSERVATIONS:

Development of fuzzing observed: Yes; No
 Color change observed: Yes; No
 Loss of cover observed: Yes; No

REMARKS: None.

RATING SYSTEM:

- Class 5 - No pilling
- Class 4 - Slight pilling
- Class 3 - Moderate pilling
- Class 2 - Severe pilling
- Class 1 - Very severe pilling



Received:01/03/2017	Completed:01/05/2017	Letter: K	TM	P.O.#:	Test Report #:	3-17055-0-
Client's Identification	Style: Step. Composition: 100% Trevira CS. Weight: 470 g/lm. Product End Use: Upholstery. Color: Grey					
Tested For: Bente Ellingsoe, Quality Department	Key Test: ASTM D 3511/ACT				140	
Gabriel A/S						
Hjulmagervej 55	Tel: 011-45-9630-3100				Ext:	
DK-9000 Aalborg, Denmark	Fax: 011-45-9811-6125					

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



 AUTHORIZED SIGNATURE
 GOVMARK
 /pm /mo

Phyllis Pettit

FEB 0 1 2017

(Page 2 of 2)