

West Yorkshire Materials Testing Service

Page 1 of 2

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 46239-01 (Amended)

Date Received: 7th March 2011

Client's Description: Sample of Fabric Art. Gaja C2C

TEST REPORT

Test Required: Fire Test

FIRE TESTS ACCORDING TO BS 476: PART 7: 1987 (AS AMENDED) (Method for classification of the surface spread of flame of products)

Date of Test: 24/06/2011

Conditioning

The sample was conditioned to constant mass at a temperature of 23 +/- 2°C and a relative humidity of 50 +/- 10% and maintained in this condition until required for testing.

Procedure

The test was carried out in accordance with BS 476: Part 7: 1987. The specimens were tested stuck down onto 12 mm calcium silicate board using PVA adhesive.

The following were recorded:-

- the time at which the flame front crosses each vertical reference line;
- the maximum extent of flame spread during the first 1.5 min from the start of the test;
- the maximum extent of flame spread during the whole test i.e. 10 min or less (if applicable)
- the time (and distance) at which maximum flame spread is reached.


The flame spread at 1.5 min and the final flame spread results were compared with the standard class limits and a classification was assigned.

-----End of Page -----


This is hereby certified to be a correct return of the tests made of the items referred to herein.

G Briggs, Head of Laboratory, Date of original 6th July 2011
Date of 1st amendment 16th November 2011
Date of 2nd amendment 1st December 2011

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.



* This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 46239-01 (Amended)

Requirements

The class limits for flamespread, detailed in BS 476: Part 7: are set out below

	Flame spread at 1.5 min (mm)	Final flame spread (mm)
Class 1	165 (+ 25)	165 (+ 25)
Class 2	215 (+ 25)	455 (+ 45)
Class 3	265 (+ 25)	710 (+ 75)
Class 4	Exceeding Class 3 limits	

A definitive classification is based on a sample of six specimens and the figure in brackets gives the tolerance by which only one specimen in six may exceed the class limit assigned.

Results

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Time for flame Spread to reach (s) (mm)					Flame spread at 1.5 min (mm)	Maximum flame spread (mm)	Time to reach maximum flame spread (s)
165	215	265	455	710			
					70	70	60
					70	70	60
					70	70	60
					70	70	60
					70	70	60
					70	70	60

The results indicate that the sample met the performance requirements of Class I.


Subcontracted test made by a UKAS Accredited Laboratory.

-----End of Document -----

This is hereby certified to be a correct return of the tests made of the items referred to herein.

G Briggs, Head of Laboratory, Date of original 6th July 2011
Date of 1st amendment 16th November 2011
Date of 2nd amendment 1st December 2011

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.



* This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.