

West Yorkshire Materials Testing Service PO Box 5, Nepshaw lane South, Morley, Leeds LS27 0QP

Tel: 0113 253 0241 Fax: 0113 252 7029 Head of Laboratory: G. Briggs C. Text ATI

Client: Gabriel

> Hjulmagervej 55 Postbox 59 DK-9100 Aalborg

Denmark

**Entry No:** 62756-02

Date received: 22/11/2013

Client's Description: 12 samples of fabric 2426 Breeze Fusion:- 4101, 4201, 4804, 4601, 4603, 4604,

4301, 4302, 4401, 4501, 4502, 4004

## **TEST REPORT**

**Test Required:** Colour Fastness to Rubbing

Date of Test: 5.12.13 to 12.12.13

Method of Test: BS EN ISO 105 - X12: 2002

		<u>Dry</u>	<u>Wet</u>
<u>Staining</u>			
4101:-	Warp	5	5
	Weft	5	5
4201:-	Warp	5	5
	Weft	5	5
4804:-	Warp	5	5
	Weft	5	5
4601:-	Warp	5	5
	Weft	5	5
4603:-	Warp	5	5
	Weft	5	4-5
4604:-	Warp	5	5
	Weft	5	5
4301:-	Warp	5	5
	Weft	5	5

This is hereby certified to be a correct return of the tests made of the items referred to herein.







Geoff Briggs C.Text., A.T.I. Head of laboratory 6<sup>th</sup> May 2014

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- Test marked (\*) in this certificate are not included in the UKAS Accreditation
- Schedule for this Laboratory.

  Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.





West Yorkshire Materials Testing Service PO Box 5, Nepshaw lane South, Morley, Leeds LS27 0QP

Tel: 0113 253 0241 Fax: 0113 252 7029 Head of Laboratory: G. Briggs C. Text ATI

Client: Gabriel

> Hjulmagervej 55 Postbox 59 DK-9100 Aalborg Denmark

**Entry No:** 62756-02

Staining		<u>Dry</u>	Wet
4302:-	Warp	5	5
	Weft	5	5
4401:-	Warp	5	4-5
	Weft	5	4-5
4501:-	Warp	5	5
	Weft	5	5
4502:-	Warp	5	5
	Weft	5	5
4004:-	Warp	5	5
	Weft	5	5
Change in color	<u>ur</u>		
All 12 Fabrics:-	Warp Weft	<u>Dry</u> 5 5	<u>Wet</u> 5 5

Note: Change in colour is not a requirement of the method but was carried out at the request of the client.

-----End of Document------

This is hereby certified to be a correct return of the tests made of the items referred to herein.







Geoff Briggs C.Text., A.T.I. Head of laboratory 6th May 2014

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.

  Opinions and interpretations expressed herein are outside the scope of UKAS
- accreditation.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

