

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Received: 02/19/2018 | Completed: 02/21/2018 | Letter: W7 RV | P.O.#: Test Report #: 3-24609-7-Client's Style: 2428 Harmony. Date of Mfg.: 15-02-2018. Composition: 85% Wools of New Zealand/ 15% Polyamide. Weight: Identification 480 g/lm. (see continuation) Tested For: Bente Ellingsoe, Quality Department Key Test: AATCC 15 175 Gabriel A/S Hjulmagervej 55 Tel: 011-45-9630-3100 Ext: DK-9000 Aalborg, Denmark Fax: 011-45-9811-6125

CLIENT'S IDENTIFICATION (continuation):

[Color as Described by SGS Govmark: Light Blue]. Product End Use: Upholstery. Additional Information: col: 3103.

LE: 2013; V 05/16

PC: NS

TEST PERFORMED: AATCC Test Method 15 - Colorfastness to Perspiration

RESULTS:

Rating

1. Color change of sample --

Evaluated by comparison with:

Grade 5

AATCC Gray Scale for Color Change

2. Staining on multi-fiber #42 transfer cloth (6 fiber wide band) --

Evaluated by comparison with:

[] AATCC Chromatic Transference Scale

[x] AATCC Gray Scale for Staining

FIBER: Acetate Grade 5 Cotton Grade 5 Nylon Grade 5 Polyester Grade 5 Acrylic Grade 5 Wool Grade 5

NOTE: This test method is based on the use of an acid solution. Previous editions specified both acid and alkaline solutions. The alkaline solution has been eliminated from the test method.

REMARKS: None.

RATING SYSTEM:

Grade 5 - No color change or transfer

Grade 4 - Slight color change or transfer

Grade 3 - Noticeable color change or transfer

Grade 2 - Considerable color change or transfer

Grade 1 - Severe color change or transfer

ACCEPTANCE CRITERIA: None cited.

CONCLUSION: Not applicable.

(Page 1 of 2)



96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Page 2

							Page 2
Received:02/19/2	2018 Completed: 02/21/2018	Letter: W7	RV	P.O.#:	Test Report #:		3-24609-7-
	Style: 2428 Harmony. Date of New Style. (see continuation)	Mfg.: 15-02-2018	8. Con	nposition: 85% Wools of N	ew Zealand/ 15% Po	olyamide	. Weight:
Tested For: Bente Ellingsoe, Quality Department Gabriel A/S				Key Test: AATCC 15			175
	ılmagervej 55 -9000 Aalborg, Denmark				-45-9630-3100 -45-9811-6125	Ext:	
CERTIFICATION	N: I certify that the cedures and equipment s			re obtained after te:	sting specimens	in acc	ordance
MIT		Phyllis Pe	ttit				

AUTHORIZED SIGNATURE GOVMARK /mg

/pm

MAR 1 2 2018

(Page 2 of 2)