

West Yorkshire Materials Testing Service PO Box 5, Nepshaw lane South, Morley,

Leeds LS27 0QP

Tel: 0113 253 0241 Fax: 0113 252 7029 Head of Laboratory: G. Briggs C. Text ATI

Client: Gabriel

Hjulmagervej 55 Postbox 59 DK-9100 Aalborg

Denmark

**Entry No:** 56674-02

**Date received:** 08/02/2013

Client's Description: Sample of fabric 13-2446 Twist Melange Moskito: 60004 grey, 60076 light grey,

61104 beige, 62066 yellow, 63012 orange, 66018 blue, 67004 green blue, 68118

light green, 68119 yellow green

## **TEST REPORT**

**Test Required:** Colour fastness to rubbing **Date of test:** 18/03/2013 to 19/03/2013

Method of Test: BS EN ISO 105-X12:2002

| Staining: -  | <u>Dry</u> | <u>Wet</u> |
|--------------|------------|------------|
| 60004:- Warp | 5          | 5          |
| Weft         | 5          | 5          |
| 60076:- Warp | 5          | 5          |
| Weft         | 5          | 5          |
| 61104:-Warp  | 5          | 5          |
| Weft         | 5          | 5          |
| 62066:-Warp  | 5          | 5          |
| Weft         | 5          | 5          |
| 63012:-Warp  | 4-5        | 4-5        |
| Weft         | 5          | 4-5        |
| 66018:-Warp  | 5          | 5          |
| Weft         | 5          | 5          |
| 67004:-Warp  | 4-5        | 4-5        |
| Weft         | 4-5        | 4-5        |

This is hereby certified to be a correct return of the tests made of the items referred to herein.





Briggs

Geoff Briggs C.Text., A.T.I. Head of laboratory 25/03/2013

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.





West Yorkshire Materials Testing Service PO Box 5, Nepshaw lane South, Morley, Leeds LS27 0QP

Tel: 0113 253 0241 Fax: 0113 252 7029 Head of Laboratory: G. Briggs C. Text ATI

Client: Gabriel

Hjulmagervej 55 Postbox 59 DK-9100 Aalborg

Denmark

**Entry No:** 56674-02

|             | <u>Dry</u> | <u>Wet</u> |
|-------------|------------|------------|
| 68118:-Warp | 5          | 5          |
| Weft        | 5          | 5          |
| 68119:-Warp | 5          | 4-5        |
| Weft        | 5          | 4-5        |

| Change in colour: - | <u>Dry</u> | Wet |
|---------------------|------------|-----|
| All samples:-Warp   | 5          | 5   |
| Weft                | 5          | 5   |

Change in colour is not a requirement of the method but was carried out at the request of the client.

This is hereby certified to be a correct return of the tests made of the items referred to herein.





Geoff Briggs C.Text., A.T.I. Head of laboratory 25/03/2013

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.

  Opinions and interpretations expressed herein are outside the scope of UKAS
- accreditation.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

