



Report 73027 Test Report



Applicant

GABRIEL A/S
Hjulmagervej 55
9000 Aalborg
DÄNEMARK

Reference

BEA - ÖTI 280114
Mrs. Bente Ellingsoe

Application

Determination of burning behaviour.

Test Material

"Fame"

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

Issuing and Signatures

Number of pages contained: 4

Original Issue / Vienna 2014-02-24 / da/KK 684

Authorised for Institute
Ing. Franz Lenz



Contents

1	Order.....	2
1.1	Chronology.....	2
1.2	Samples.....	2
2	Findings / Tests performed.....	2
2.1	Description of the specimen.....	2
2.2	Determination of burning behaviour of upholstery fabrics.....	3
3	Remarks.....	4

1 Order

1.1 Chronology

<i>Date</i>	<i>Received</i>	<i>Order</i>
2014-01-28	2014-02-04	Determination of burning behaviour.

1.2 Samples

<i>No.</i>	<i>Received</i>	<i>Sample Identification</i>
1	2014-02-03 (1)	"Fame"

(1) Samples provided by the customer. (2) Sample drawn by ÖTI.

2 Findings / Tests performed

2.1 Description of the specimen

Description of the specimen according to DIN 60 000

Test results

Tested sample: 1

Type of fibre according to DIN 60 001 part 1 and DIN ISO 2076	95% Wool 5% Polyamide (declaration by the applicant)
Technological description	woven fabric



2.2 Determination of burning behaviour of upholstery fabrics

Test conditions

According to ÖNORM B 3825 ^{accr.})

Arrangement of upholstery: Arrangement A: free chosen upholstery

Kind of upholstery: foam: polyurethan foam , properties: Burning behaviour: "schwerbrennbar" according to ÖNORM A 3800-1, Designation: RF 5560, Producer: Eurofoam

Number of test specimens: Longitudinal direction 3 / Cross direction 3

Test results

Tested sample: 1

Specimen	Burning-time [s]	After-flame-time [s]	After-glow-time [s]	Flame spread rate [mm/s]	self-extinguishing before reaching the mark
Longitudinal direction					
1	none	0	0	--	yes
2	none	0	0	--	yes
3	none	1	0	--	yes
Cross direction					
1	none	1	0	--	yes
2	none	10	0	--	yes
3	none	8	0	--	yes

Secondary effects of burning:

melting of the specimen within the inflammation-area

behaviour of the covering fabric: self-extinguished

behaviour of the upholstery: self-extinguished

Opinion

According to ÖNORM B 3825 the tested specimen can be classified as

"schwerbrennbar gemäß ÖNORM B 3825"

Comments:

This test is a compound test at which the furniture fabric will always be tested combined with upholstery. Classification, therefore, relates only to the described arrangement of specimens and foam used.



3 Remarks

Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or the ÖTI.

The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product produced unchanged.

Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

Sample Material

Results of performed tests only refer to the sample material provided.

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

Quality management, Accreditation and Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025 respectively EN ISO/IEC 17065.



The ÖTI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/nando/>). Accreditation as Testing Laboratory was provided by Akkreditierung Austria (Federal Ministry of Economy, Family and Youth). The scope of accreditation is listed on www.bmwfj.gv.at/akkreditierung.

In this report test conditions of individual accredited test procedures are marked with *accr.*)

According to the decree on the use of the accreditation mark ("AkkZV") the accreditation mark is only to be used by the accredited Conformity Assessment Body.

Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of PSA-SV § 10, BGBl. Nr. 596/1994 as amended and article 13 of the Directive 89/686/EEC have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

.Copyright und Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.